

Premalube Xtreme Heat Shield

MEGA DISTRIBUTORS

Extreme Temperature Grease



The only patented grease specifically formulated to protect equipment exposed to extremely high temperatures.

Provides superior protection for equipment against extreme heat, contaminants and heavy loads.

PRODUCT OF CHOICE FOR EXTREME TEMPERATURE APPLICATIONS

Provides Superior Equipment Protection for:

Brick Plants	Steel Mills
Asphalt Plants	Mining
Glass Manufacturing	Forges and Foundries
Kilns, Furnaces, and Ovens	

Premalube Xtreme Heat Shield Meets or Exceeds these Performance Requirements:

- US Steel Mill Grease Specifications:
 - Roll Neck Grease, Req. No. 340
 - Extreme Pressure Grease Req. No. 350
 - Extra Duty EP Grease. Req. No. 352
 - Extreme-Temp. Req. No. 355, 370 & 372
 - Ball and Roller Bearing, Req. No. 371
 - Mill Utility Grease Req. No. 375
- Military Spec. MIL-G-23549C, MIL-G-2345C
- Federal Specification VV-G-632a
- Caterpillar MPGM
- Chrysler MS 3551E (Part # 2264833)
- General Motors Specification GM 6031-M
- DIN 51 825, DIN 51 818

Features and Benefits

- Extreme temperature performance up to 1000°C intermittent with monitored lubrication intervals
- Patented* Calcium Sulfonate Grease with High Moly and Graphite Content
- Prolongs Bearing and Equipment Life
- Extends Lubrication Intervals by Up to 10 Times
- Excellent High Temperature Performance - Protects up to 1000°C Intermittently.
- At Temperatures Above 320°C the Premium Base Oil Evaporates Cleanly Leaving Solid Lubricants Behind to Protect Equipment

WARNING: Consult the label for full instructions and precautions before using this product.

MEGA DISTRIBUTORS

PO Box 10185
North Shore Mail Centre
Auckland 0745
Phone: 09 473 6505
Fax: 09 473 6501
Email: sales@megadistributors.co.nz

www.megadistributors.co.nz



Premalube Xtreme Heat Shield

MEGA DISTRIBUTORS

Extreme Temperature Grease

Additives	User Benefits
Contains a total additive package for outstanding long-term performance.	
Premium Grade Base Oil	Superior grade, highly refined base oil resists oxidation, hardening and high temperature breakdown to maintain better lubricity
Calcium Sulfonate Base	Withstands high heat and provides additional extreme pressure protection under heavy loads. Extremely water resistant, heavier than water to resist washouts even in submerged environments. Adhesive and Cohesive Polymers, Tackiness Agents: Highly-elastic polymers hold grease together and in place to reduce squeezeout, channelling and sling-off. Prevents loss of lubricant that leaves bearings "starved".
Rust and Corrosion Inhibitors	Blocks out corrosive elements such as acids, water, condensate and steam by forming a protective barrier on equipment surfaces to prevent chemical wear.
Extreme Pressure (EP) Agents	A heat seeking additive that prevents the cold welding that can occur under heavy loads. Minimizes wear while helping equipment run cooler.
Anti-Wear and Friction Reducing Additives	Prevents metal-to-metal contact, two-surface wear, vibration and chatter. Keeps high friction surfaces, such as bearings, properly lubricated to prevent metal loss, downtime, and replacement expenses.
Oxidation Inhibitors	Extends lubricant service life by retarding the oxidation process. Provides a chemical shield that prevents the oxidizing effects of oxygen and water. Shock Load Reducers Cushions impact to minimize the stress, vibration and chatter that can occur under heavy loads and during start-stop operations.
Molybdenum Disulfide	Plates metal surface asperities completely with a premium lubricant coating that withstands high pressures, heavy loads and shear conditions. Reduces abrasive wear, too.
Graphite	High concentration offers extreme temperature protection and stability while guarding against contaminants, heavy loads, and water washout.

Physical Properties	Premalube Xtreme Heat Shield
Penetration ASTM D 217	330
Multistroke penetration ASTM D 217	335
Four-ball Index ASTM D 2596	101
Four-ball (weld) ASTM D 2596	1000+
Four-ball (wear scar) ASTM D 2596	0.341
Timken method ASTM D 2509	70
Rust test ASTM D 1743	Pass
Copper corrosion ASTM D 130	1B
Low Temperature Limit C	-6
High Temperature Limit C	1093
Base Oil Viscosity @40C	113
Base Oil Viscosity @100C	12.1
Base Oil Viscosity Index	96

Ideal for use on extreme heat applications including	
Brick plants	Kiln cars
Furnaces	Ovens
Steel mills	Asphalt plants
Mining	Glass manufacturing
Forges and foundries	etc

Note: Equipment operated continuously above 320°C will require frequent monitoring and re-lubrication.

MEGA DISTRIBUTORS

PO Box 10185
 North Shore Mail Centre
 Auckland 0745
 Phone: 09 473 6505
 Fax: 09 473 6501
 Email: sales@megadistributors.co.nz

www.megadistributors.co.nz

